

J52-08-226 Polyethylene Copolymer

J52-08-226 is a bimodal high molecular weight high density polyethylene copolymer designed for thin gauge blown film applications where good processability, high stiffness and excellent strength are required such as: Grocery sacks, T-Shirt bags, Institutional/Industrial Can Liners, Roll Stock, Produce Bags, Heavy Duty Bags and Deli Wrap.

J52-08-226 meets the requirements of the U.S. Food and Drug Administration of 21 CFR 177.1520 covering the safe use of articles intended for use in food contact applications.¹

Typical Properties²

		Values English Units	SI Units	ASTM Method
Resin				
Density		—	0.951 g/cc	D4883
Melt Index 190°C/5.0 kg		—	0.31 g/10 min	D1238
Melt Index 190°C/ 21.6 kg		—	9.0 g/10 min	D1238
Compression Molded Sample				
Vicat Softening Point		255 °F	124 °C	D1525
Environmental Stress Crack Resistance				D1693
Condition B, 100% Igepal, F50 (hrs.)		> 1,500	> 1,500	
Film³				
Dart Drop Impact Strength, F50		—	350 g	D1709
Elmendorf Tear Strength	MD	—	18 g	D1922
	TD	—	180 g	
Tensile Strength @ Yield	MD	5,000 psi	34.5 MPa	D882
	TD	4,500 psi	31.0 MPa	
Tensile Strength @ Break	MD	10,000 psi	69.0 MPa	D882
	TD	9,000 psi	62.0 MPa	
Elongation @ Break	MD	300 %	300 %	D882
	TD	500 %	500 %	
Secant Modulus (2%)	MD	135,000 psi	930 MPa	D882
	TD	150,000 psi	1035 MPa	

¹ Specific limitations may apply. Consult the J52-08-226 Regulatory Position Statement for more information.

² Typical property values will vary and are not to be used as specification limits.

³ Film property data based on 0.6 mil film (15 micron) obtained under laboratory conditions at a 4:1 Blow-Up-Ratio (BUR) and stalk height of 7x die diameter. Actual film properties may vary depending on extrusion equipment and processing conditions.

Revision: 1/2021

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of the this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.

2600 South Shore Boulevard
League City, TX 77573
Tel: 281-535-6600
www.ineos-op.com

INEOS
Olefins & Polymers USA

J52-08-226 Polyethylene Copolymer

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices.

For further information, call + 1-800-527-5419.

Health and Safety Information

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Material Safety Data Sheet (MSDS) contains the available product health and safety information for this material and can be found at www.ineos-op.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

The Material Safety Data Sheet for this product contains shipping descriptions and should be consulted, before transportation, as a reference in determining the proper shipping description. If the material shipped by INEOS is altered or modified, different shipping descriptions may apply and the MSDS of the original material should not be used.

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of the this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.