

Technical Information



DOW™ LDPE 780E

Low Density Polyethylene Resin

Overview

LDPE 780E Low Density Polyethylene Resin can be readily processed using conventional injection moulding techniques utilising melt temperatures between 140 and 250°C, a mould temperature between 10 and 50°C, and injection pressure between 50 and 150 MPa.

When properly injection moulded, 780E Low Density Polyethylene Resin exhibit:

- Excellent flow
- Good rigidity
- Good surface gloss

Note: LDPE 780E Low Density Polyethylene Resin should comply with FDA regulation 177.1520 and with most European food contact regulations when used unmodified and processed according to good manufacturing practices for contact applications. Please, contact your nearest Dow office for food contact compliance statements. The purchaser remains responsible for determining whether the use complies with all relevant regulations.

Applications:

- Housewares.
- Toys & leasures.
- Containers.
- Compounding.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.923 g/cm ³	0.923 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	20 g/10 min	20 g/10 min	ISO 1133
Molding Shrinkage			ASTM D955
Flow	0.023 in/in	2.3 %	
Across Flow	0.015 in/in	1.5 %	
Environmental Stress-Cracking Resistance			ASTM D1693
Compression Molded	1.40 hr	1.40 hr	
Spiral Flow Length			Dow Method
1200 bar	3.3 in	8.50 cm	
600 bar	1.9 in	4.90 cm	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus - 2% Secant (Compression Molded)	23800 psi	164 MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield, Compression Molded	1190 psi	8.20 MPa	
Break, Compression Molded	1520 psi	10.5 MPa	
Tensile Strain (Break, Compression Molded)	50 %	50 %	ISO 527-2
Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Elongation			ASTM D882
MD: Break, 7.9 mil (200 µm)	700 %	700 %	
TD: Break, 7.9 mil (200 µm)	750 %	750 %	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Impact Strength	136 ft-lb/in ²	286 kJ/m ²	ISO 8256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Shore Hardness (Shore D)	49	49	ISO 868
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	199 °F	93.0 °C	ASTM D1525

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

Additional Information

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

North America	Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369	+32-3-450-2240
	1-989-832-1426	+800-783-825
Mexico:	+1-800-441-4369	
Latin America	South Africa	+800-99-5078
Argentina:	+54-11-4319-0100	
Brazil:	+55-11-5188-9000	
Colombia:	+57-1-219-6000	Asia Pacific
Mexico:	+52-55-5201-4700	+800-7776-7776
		+603-7965-5392

www.dowplastics.com

This document is intended for use within Europe

Published: 2005-05-05

© 2010 The Dow Chemical Company

