



2120H

20 MELT FLOW IMPACT COPOLYMER POLYPROPYLENE

Product Description and Applications:

Pinnacle Polymers Polypropylene 2120H is made via UNIPOL™ PP technology, which utilizes gas- phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for large buckets and other injection molding applications where toughness and cold temperature impact strength are required.

Features:

The 2120H product provides:

- Excellent cleanliness
- Superior toughness
- Excellent color and process stability
- Good melt strength
- Fast Set-up time
- UL Listed

Pinnacle's 2120H polypropylene as marketed by Pinnacle Polymers Company, in natural, uncolored pellet form is covered under US FDA Food Contact Notification 864. As such, this polymer complies with the requirements of CFR Title 21 and can be used in contact with all food types under Conditions of Use A-H.

Typical Properties

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	20 g/10 min.	20 g/10 min.	D1238 ¹
Density at 23°C	0.9 g/cm ³	900 kg/m ³	D1505
Shrinkage	0.013 in/in	0.013 mm/mm	D955
Heat Deflection Temperature at 0.455 MPa (66psi)	224°F	107°C	D648
Tensile yield strength, at 51 mm/min	3500 psi	24.2 MPa	D638 ²
Yield elongation, at 51 mm/min	11%	11%	D638 ²
Flexural modulus (1% secant) at 1.27 mm/min	180,000 psi	1242 MPa	D790A ²
Notched Izod impact strength, at 73°F/23°C	3.5 ft-lb/in	187 J/m 18.3 kJ/m ²	D256 ²
Gardner Impact strength at -22°F/-30°C	150 in-lb	16.5 J	D5420 ³

¹Condition L 230/2.16

²ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

³Method G, Geometry GC

UNIPOL is a trademark of W. R. Grace and Co.

FDA and SDS documents are available on our website at: <http://www.pinnaclepolymers.com/datasds.php>

Technical data contained herein is furnished without fee or obligation, and is given and accepted at recipient's sole risk. Since conditions of use may vary and are beyond our control, Pinnacle Polymers makes no representation about and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects, industrial hygiene requirements, or other matters associated with particular application of any product described herein. Pinnacle Polymers disclaims any warranty, expressed or implied, regarding the information contained herein, including the implied warranty of merchantability of fitness for a particular purpose. 010518