



Technical Data Sheet

PP H350 GP/7

Polypropylene Homopolymer

PRODUCT DESCRIPTION

PP H350 GP/7 is a polypropylene homopolymer with narrow molecular weight distribution. The product has an optimal stabilization package and an advantageous combination of high fluidity and good stiffness.

TYPICAL APPLICATIONS

PP H350 GP/7 is recommended for Injection Molding general purpose applications such as furniture and various household articles. It is also used in Compounding as a blending material and compounding base.

Properties	Conditions	Method	Typical values*	Units
Rheology				
Melt Flow Rate	230 °C/2.16 kg	ISO 1133	35	g/10 min
Mechanical				
Tensile Stress at Yield	50 mm/min	ISO 527	34	MPa
Elongation at Yield	50 mm/min	ISO 527	8	%
Flexural Modulus	2 mm/min	ISO 178	1200	MPa

*The values given are typical values measured on the product. These values should not be considered as specification.

REACH Statement

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered.

«Kazakhstan Petrochemical Industries Inc.» LLP is committed to fully respect REACH legislation and to use only REACH compliant raw materials.

Safety

See MSDS