



Luban DMDZ-6147 High Density Polyethylene

Description

Description

Luban DMDZ-6147 is high-density polyethylene with broad molecular weight distribution and high molecular weight. This product provides an excellent combination of extrudability and parison stability, which contribute to uniform wall thickness in large parts. The grade is ideal for blow molding containers such as the 5 - 55 gallon (20 - 210 lit) closed head shipping containers and other similar parts. The broad distribution also provides outstanding environmental stress crack resistance (ESCR) at a good rigidity. The smooth surface of molded parts is readily treated and printed for high quality applications.

Main Characteristics:

- Hexene High Density Resin
- Outstanding environmental stress crack resistance
- Excellent parison melt strength/ low sag
- Good extrudability/ processability
- Good rigidity

Application

Application

Blow molding containers from 20 lit – 210 lit for packaging of industrial chemicals, latex paints, printing inks, foodstuffs, adhesives, and other chemical specialties

Properties (Typical Values)

Property	Unit	Test method	Value
Melt Index (190°C/2.16 kg)	g/10 min	ASTM D1238	0.05
Melt Index (190°C/21.6 kg)	g/10 min	ASTM D1238	9
Density	g /cm ³	ASTM D792	0.948
Environmental Stress-Cracking Resistance 122°F (50°C), 10% Igepal, F50	hr	ASTM D1693 ¹	>1000
Flexural Modulus - 2% Secant	MPa	ASTM D790B ¹	885
Tensile stress at yield	MPa	ASTM D638 ¹	24.6
Tensile stress at break	MPa	ASTM D638 ¹	35.5
Tensile strain at break	%	ASTM D638 ¹	780
Tensile Impact Strength	kJ/m ²	ASTM D1822 ¹	462
Durometer Hardness (Shore D)		ASTM D2240 ¹	57
Deflection Temperature Under Load 0.45 MPa, Unannealed	°C	ASTM D648 ¹	66
Vicat Softening Temperature	°C	ASTM D1525	127

¹Molded and tested in accordance with ASTM D4976.

Note: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.



Luban DMDZ-6147

High Density Polyethylene

Storage and Handling

Luban DMDZ-6147 should be stored in well ventilate area during handling or processing of to prevent accumulation of dust and fumes. Avoid contact with strong oxidizers, excessive heat, sparks or open flame as this could well speed up alteration and consequently loss of quality of the material in which could lead to unforeseen dangers. The bags must be protected from direct sunlight and should be stored in shaded and completely dry area for good processing.

Safety

Luban DMDZ-6147 is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

Food Contact

Luban DMDZ-6147 meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: Mar. 2020

Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using OQ product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under OQ or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of OQ except in a writing signed by an authorized OQ employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at OQ's option, and in no event shall OQ be liable for special, consequential, incidental, punitive or exemplary damages.