

Technical Data Sheet

Lupolen 2221D

Low Density Polyethylene



Product Description

Lupolen 2221D is a fractional melt index homopolymer LDPE resin designed for film applications requiring excellent bubble stability/melt strength, impact strength, stiffness and shrink. 2221D is selected by customers for collation shrink films, pallet shrink films, packaging films and heavy duty films where processability, strength and stiffness are important. 2221D contains an antioxidant.

Regulatory Status

For regulatory compliance information, see Lupolen 2221D [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Europe
Application	Agriculture Film; Bags & Pouches; Can Liners; Clarity Film; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Shrink Film; Stretch Hood; Textile Packaging Film
Market	Flexible Packaging
Processing Method	Blown Film

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	0.25	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.9220	g/cm ³	ASTM D1505
Product Density, (23 °C)	0.9220	g/cm ³	ASTM D1505
Film			
Dart Drop Impact Strength, F50	190	g	ASTM D1709
Tensile Strength at Break			
MD	28	MPa	ASTM D882
TD	24	MPa	ASTM D882
Tensile Strength at Yield			
MD	12	MPa	ASTM D882
TD	12	MPa	ASTM D882
Tensile Elongation at Break			
MD	400	%	ASTM D882
TD	550	%	ASTM D882
1% Secant Modulus			
MD	220	MPa	ASTM D882
TD	250	MPa	ASTM D882
Elmendorf Tear Strength			
MD	170	g	ASTM D1922
TD	220	g	ASTM D1922
Optical			
Haze	7.5	%	ASTM D1003
Gloss	62		ASTM D2457

Additive

Slip	None	LYB Method
Antiblock	None	LYB Method

Notes

Data obtained from 50 micron film produced on a 50 mm extruder with a 100 mm die, 205°C melt temperature, 2.5:1 BUR, 0.635 mm die gap at 27 kg/hr.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.