

Technical Data Sheet

Chemicals



REPSOL ALCUDIA 2320FG

The grade REPSOL ALCUDIA 2320FG is a low density polyethylene grade produced by high pressure tubular technology, suitable for thin blown film or cast film applications. This material offers easy processability and good balance of mechanical and optical properties. It contains slip (550 ppm) (erucamide) and antiblock (1125 ppm).

Applications

- Shrink film.
- Automatic packaging
- Lamination.
- Film coextrusion with good optical properties

Recommended melt temperature range from 160 to 200°C. Processing conditions should be optimized for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Melt Flow Rate (190°C, 2.16 kg)	2.00	g/10 min	ISO 1133
Density at 23°C	923	kg/m ³	ISO 1183
FILM⁽¹⁾			
Dart Drop (F ₅₀)	100	g	ISO 7765-1
Tear Resistance (Elmendorf) (MD/TD)	215/230	cN	ISO 6383-2
Tensile Stress at Break (MD/TD)	19/15	MPa	ISO 527-3
Elongation at Break (MD/TD)	400/250	%	ISO 527-3
Coefficient of friction (Dynamic)	<0.1	-	ISO 8295
Gloss (45°)	60	-	ASTM D-2457
Gloss (60°)	95	-	ASTM D-2457
Haze	7.5	%	ASTM D-1003
OTHER			
Vicat Softening Temperature (load 10N)	95	°C	ISO 306

(1) 30 µm thickness film, blow up ratio 2.5:1.

[1/2]

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_polyolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

 All our
polyolefins are
recyclable

Technical Data Sheet

Chemicals



Storage

The grade REPSOL ALCUDIA 2320FG should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 50°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

Disclaimer

This grade complies with the European regulations for materials for use in food contact. This grade is not intended to be used in medical, pharmaceutical, or healthcare applications, therefore Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet
- Statement on compliance with food contact regulations

Recommended consumption period: 12 months from the raw material reception

July 2021

[2/2]

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_polyolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

 **All our
polyolefins are
recyclable**