

Technical Information

Supreme™ 001S

Polyolefin Plastomer

Introduction

Supreme™ 001S, Polyolefin Plastomer (POP), is an **ethylene-octene copolymer** produced via Nexlene™ technology. Supreme™ 001S performs well in a wide range of various food & non-food packaging films with excellent sealing property and impact strength.

Typical Performance:

- Excellent low seal initiation temperature and hot tack strength
- Superior impact strength and transparency

Complies with:

- US. FDA 21 CFR 177.1520
- EU. No 10/2011

Additives:

- Antiblock: 3500ppm
- Slip: 1300ppm

Properties

		Typical Values	Unit	Test Method	
Resin Properties	Density	0.903	g/cm ³	ASTM D792	
	Melt index (2.16 kg @190°C)	1.0	g/10min	ASTM D1238	
	Melting temperature	98	°C	SK Method	
	Vicat softening temperature	83	°C	ASTM D1525	
Film Properties	Film thickness - tested	40	µm	ASTM D374	
	Dart impact strength	>1000	g	ASTM D1709A	
	Haze	4.0	%	ASTM D1003	
	Seal initiation temperature ¹	76	°C	SK Method ¹	
	Elmendorf tear strength	MD	10	g/µm	ASTM D1922
		TD	17	g/µm	ASTM D1922
	Tensile strength at break	MD	490	kg/cm ²	ASTM D882
		TD	550	kg/cm ²	ASTM D882

Technical Information

Elongation at break	MD	610	%	ASTM D882
	TD	670	%	ASTM D882

- Extrusion Condition**
- Screw size: 55 mm
 - Die diameter: 180 mm
 - Die gap: 1.8 mm
 - Blow-up ratio: 2.1
 - Melt temperature: 160-180 °C

¹ Temperature at which 0.4 kg/25.4 mm heat seal strength is achieved

Notes

These are **typical values** and are **not be construed as specifications**. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.

For additional sales, order and technical assistance

Head office SK Global Chemical Co.,LTD
26 Jong-ro, Jongno-gu,
Seoul, Korea
TEL +82-2-2121-5052

TS&D SK innovation Global Technology
325 Exporo, Yueseong-gu,
Daejeon, Korea
TEL +82-42-609-8623