



LQ-Y35

TECHNICAL DATA SHEET

PP LQ-Y35

TYPICAL APPLICATIONS:

Thin-wall packaging; non-woven fabrics etc.

PROPERTY	VALUE	UNIT	ASTM
Density (23℃)	0.905	g/cm ³	GB/T 1533
MFR (190℃/2.16kg)	35	g/10min	GB/T 3682
Tensile Stress at Yield	≥30	MPa	GB/T 1040.2-2006
Elongation at Break	≥15	%	GB/T 1040.2-2006
Isotactic index	≥95	%	GB/T 2412
OIT(210℃,A1)	>9	min	GB/T 9366

Note: the above data are only typical analysis values, not product specifications, customer should confirm the suitability and results through their own testing.

PACKING:

FFS Bag: 25kg/bag

MATTERS NEED ATTENTION:

Products should be stored in a well-ventilated, dry, clean warehouse with good fire protection facilities. When storing, it should be kept away from heat source and prevent direct sunlight. It is strictly prohibited to pile up in the open air.