

Technical Data for TURKMENPLENE

(POLYPROPYLENE)

Typical Properties	Unit	Product Grade			
		TPP D 30 S	TPP F 79 FB	TPP D 382 BF	TEST Method
Melting Rate	g/10min	3.2	12.5	3.2	ISO 1133
Non Soluble in Xylol	% by weight	95.7	96	95.7	MA 15558
Ash (as oxides)	ppm by weight	130	130	130	MA 16013
Chlorine	ppm by weight	35	35	35	MA 15794
Ultimate Tensile Strength (in yeild strength)	Mpa not less than	33	33	33	ISO 527
Flexural Strength Modulus	not less than	1300	1390	1300	ISO 178
Impact Strength with cut by IZOD at 23C	J/m not less than	3.5	3.5	3.5	ISO 180/1A
Index of Yellowing	not less than	2	2	2	MA 17212
Product Types		Yarn	Fibre	Film	

arks : Technical Datra are intended for advertising purposes only
Indicated parameterrrs are not guaranteed