



NATPET

Teldene® R40MLC LyondellBasell licensed Spheripol Process
POLYPROPYLENE RANDOM COPOLYMER

Technical Data Sheet

Typical Applications

- Suitable for high clarity injection molding and Injection-Stretch Blow Molding (ISBM) applications
- Used for the production of housewares and cosmetic packaging, TWIM articles for food and non-food applications, caps & closures and component parts for automotive industry

Key Characteristics

- Organoleptically suitable for food contact
- Nucleated random copolymer, contains anti-static agent
- Excellent processability and flow-ability
- Excellent transparency and dimensional stability
- Good impact resistance
- Reactor grade, no per-oxide added
- Food contact approval for specific applications (refer to **NATPET**)

Processing Methods

- Injection Molding

Resin	Conditions	Method	Value	Unit
Density	23°C	ISO 1183	0.900	g/cm ³
Melt Flow Rate (MFR)	230°C/2.16 kg	ASTM D 1238-13	40	g/10-min
Mechanical				
Flexural Modulus		ISO 178	1,100	MPa
Tensile Stress at Yield	50-mm/min	ISO 527	29	MPa
Tensile Strain at Break	50-mm/min	ISO 527	> 50	%
Tensile Strain at Yield	50-mm/min	ISO 527	12	%
Thermal				
Heat Deflection Temperature	0.45 MPa Un-annealed	ISO 75B	73	°C
Vicat Softening Temperature	A50 (50°C/h 10N)	ISO 306	125	°C
Additional				
Tensile Modulus	1-mm/min	ISO 527	1,000	MPa
Izod <i>Notched</i>	23°C	ISO 180	5.4	kJ/m ²
Haze	1.0 mm	ASTM D 1003	9.0	%

Technical information

Note: The above are typical data representing the product; not to be construed as analysis certificate or specifications.

DS v1.0

For further details about **NATPET** and its products, please visit the website at www.natpet.com

NATPET® products, marketed under the trade name Teldene®, are intended for the use by those customers and/or any other consumers, who undertake to become responsible to independently establish on their own the appropriateness of the product for its intended use, covering all safety and legally enacted requirements at the location of its projected use and the legal disposal practices thereof. The description of the product as given in this sheet shall under no circumstances be construed as warranty, express or implied including a warranty of merchandize fitness for a particular purpose. On behalf of NATPET, no one is authorized to make any such warranties, or take up on their own to assume such a liability. In case of product related claims, the sole and maximum remedy will be the physical substitution of the product or reimbursement of the purchase value, as per NATPET's options. Further claims based on consequential, secondary, castigatory, or extraordinary damages will in no way entertained by NATPET.

NATPET would like to advise its customers and other users that unless specifically stated the supplied products should not be used for applications in medical and/or pharmaceutical sectors.

**NATPET****Teldene® R40MLC** LyondellBasell licensed Spheripol Process
POLYPROPYLENE RANDOM COPOLYMER

Technical Data Sheet

Special Features

- Amazing result on transparent articles
- Shows broad processing window with excellent clarity

Processing Conditions

Average extruder temperature range may be kept between 210 - 245°C.

Food Regulation

This product is defined as a preparation under specific food contact regulation. Detailed information will be provided in a relevant document "Regulatory Compliances Product Declaration" upon request.

Storage and Handling

Polypropylene resin should be stored to prevent a direct exposure to sunlight and heat. The Product estimated shelf life is one year starting from production date, adequate humidity below 80%, and temperature below 40°C. Customers might not fully follow the optimal storage condition, hence the shelf life recommended at customer site is six months only as received. Please refer to "Material Safety Datasheet" (MSDS) for handling and storage information.

Documents

Specific documents MSDS and RCPD are available on request. Please send your request to the following e-mail: pa@natpet.com or visit our website : WWW.natpet.com

POLYPROPYLENE RANDOM COPOLYMER

DS v1.0

For further details about **NATPET** and its products, please visit the website at www.natpet.com

NATPET® products, marketed under the trade name Teldene®, are intended for the use by those customers and/or any other consumers, who undertake to become responsible to independently establish on their own the appropriateness of the product for its intended use, covering all safety and legally enacted requirements at the location of its projected use and the legal disposal practices thereof. The description of the product as given in this sheet shall under no circumstances be construed as warranty, express or implied including a warranty of merchandise fitness for a particular purpose. On behalf of NATPET, no one is authorized to make any such warranties, or take up on their own to assume such a liability. In case of product related claims, the sole and maximum remedy will be the physical substitution of the product or reimbursement of the purchase value, as per NATPET's options. Further claims based on consequential, secondary, castigatory, or extraordinary damages will in no way entertained by NATPET.

NATPET would like to advise its customers and other users that unless specifically stated the supplied products should not be used for applications in medical and/or pharmaceutical sectors.